STYROLUTION GROUP GMBH

ERLENSTRASSE 2, FRANKFURT AM MAIN 60325 DE

Terluran or Novodur: GP-22

I

Acrylonitrile Butadiene Styrene (ABS), pellets

Flammability	Value	Test Method
Flame Rating		
0.800 mm, ALL	HB	UL 94
1.50 mm, ALL	HB	UL 94
3.00 mm, ALL	HB	UL 94
3.00 mm, ALL	HB40	IEC 60695-11-10, -20
0.800 mm, ALL	HB75	IEC 60695-11-10, -20
1.50 mm, ALL	HB75	IEC 60695-11-10, -20
Glow Wire Flammability Index		IEC 60695-2-12
0.800 mm	650 °C	
1.50 mm	650 °C	
3.00 mm	650 °C	
Glow Wire Ignition Temperature		IEC 60695-2-13
0.800 mm	675 °C	
1.50 mm	675 °C	
3.00 mm	675 °C	
Electrical	Value	Test Method
Hot-wire Ignition (HWI)		UL 746
0.800 mm	PLC 3	
1.50 mm	PLC 3	
3.00 mm	PLC 3	
High Amp Arc Ignition (HAI)		UL 746
0.800 mm	PLC 1	
1.50 mm	PLC 1	
3.00 mm	PLC 0	
Comparative Tracking Index (CTI)	PLC 0	UL 746
High Voltage Arc Tracking Rate (HVTR)	PLC 1	UL 746
Volume Resistivity	1.0E+16 ohm∙cm	ASTM D257 IEC 60093
Arc Resistance	PLC 1	ASTM D495
Thermal	Value	Test Method
RTI Elec		UL 746
0.800 mm	90.0 °C	
1.50 mm	90.0 °C	
3.00 mm	90.0 °C	
RTI Imp		UL 746
0.800 mm	80.0 °C	
1.50 mm	80.0 °C	
3.00 mm	80.0 °C	

Page 1 of 2	Form Number: E108538-21871
UL and the UL logo are trademarks of UL LLC Copyright © 2014 All Rights Reserved. www.ul.com	Report Date: 5/1/200
	Last Revised: 12/13/201

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.



Component - Plastics

File Number: E108538

Report Date: 5/1/2000 Last Revised: 12/13/2012

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Thermal	Value	Test Method
RTI Str		UL 746
0.800 mm	95.0 °C	
1.50 mm	95.0 °C	
3.00 mm	95.0 °C	

Notice of Disclaimer

Page 2 of 2

By accessing this Yellow Card data information sheet and the database from which this information was generated (the "Yellow Card"), the user acknowledges and accepts the terms and conditions upon which this Yellow Card is made available. This Yellow Card, the database from which it was generated, and all related materials, support, and services, are made available by UL for use only by permission and "as is", without any representation or warranty of any kind, express or implied, including but not limited to any implied warranties of merchantability, fitness for a particular purpose or that the products identified in this Yellow Card will satisfy the user's requirements. UL cannot and does not warrant that the data contained in this Yellow Card is current, accurate, or complete. The user must independently confirm the conformance of any product to the applicable standards or requirements with the manufacturer of that product. Permission to access this Yellow Card may be withdrawn at any time by UL in its sole discretion. The identification of products and companies on this Yellow Card does not in any way imply endorsement of those products or companies by UL. UL does not assume and expressly disclaims, liability to any person for any loss or damage (including lost profits, lost savings, or any indirect, special, incidental, consequential or punitive damages whether or not UL has been advised of the possibility of such damages) arising out of, or in connection with, the use of this Yellow Card regardless of the cause or causes of such loss or damage.